

COELAN Anti-Slip

Technical Data Sheet

(Issue: 2023-03-14)

Application areas:

Glass powder for full or partial scattering into various COELAN coating systems to increase anti-slip properties.

Colour / Gloss:

transparent

Product features:

• Glass powder 105 - 210 μ

Package size

0,3 kg tin

Material consumption:

• According to requirements

Shelf Life:

Store in closed original containers in dry rooms.

Disposal

Disposal when liquid:

/

Disposal when cured:

EAK 17 02 03

Substrate:

- COELAN Anti-Slip can be applied to existing COELAN Coating systems using a coloured or transparent layer of adhesive.
- For further information on substrate pre-treatment and application, please refer to the separate technical data sheets and the application instructions.

Application temperature:

Material, atmospheric and surface temperature: at least $+5^{\circ}$ C to max. $+30^{\circ}$ C.

Relative humidity: < 80 %

The substrate temperature must be at least 3 K above dew-point temperature.

Application Instructions:

- The existing COELAN coating can be activated withKEMCO LE Flexo Adhesive Primer or COELAN Flexo Primer LE for boat coatings (see corresponding technical information).
- Apply transparent or colour adhesive layer (approx. consumption 250 g/m²).
- Full or partial coverage with COELAN Anti-Slip.

During and after the application, please ensure even and continuous ventilation in oder to guarantee a uniform drying process.

For additional information, please refer to the system product's respective Technical Data Sheets and work instructions.

Important notice

Based on our experience and to the best of our knowledge, this technical data is up to date and all information is current. As there might be operating conditions of which we have no knowledge and cannot have any knowledge, this data sheet shall be considered for information only and without responsibility. For the benefit of technical advances and the outcome of such advances, we reserve the right to make changes to the data without any prior notification. With the issuance of this publication, all prior technical information shall be considered null and void. When you contact us, you have the option to take advantage of our technical service constultants to find out about the various applications. Please be advised that all agreements and/ or confirmation smust be made in writing. Please ensure to request a written confirmation after receiving a verbal statement. For the rest, our terms and payment conditions apply.